



NOTES:

1. Water-resistive Barrier - One layer of No. 15 asphalt felt, free from holes and breaks. It shall be applied horizontally, with the upper layer lapped over the lower layer not less than 2 inches. Where joints occur, felt shall be lapped not less than 6 inches. (R703.2)
2. Lath - All lath and lath attachments shall be of corrosion-resistant materials. Lath shall be attached with 1 1/2" long, 11 gage nails, or 7/8" long, 16 gage staples, spaced at no more than 6 inches. (R703.6.1)
3. Application - Each coat shall be kept in a moist condition for at least 48 hours prior to the application of the next coat. (R703.6.4)
4. Curing - The finish coat shall not be applied sooner than seven days after application of the second coat. (R703.6.5)
5. Weep Screed - A minimum No. 26 galvanized sheet gage, corrosion-resistant weep screed or plastic weep screed, with a minimum vertical attachment flange of 3 1/2 inches shall be provided at or below the foundation plate line. The weep screed shall be placed a minimum of 4 inches above the earth or 2 inches above paved areas. (R703.6.2.1)



STANDARD DRAWING

CITY OF HOUSTON
DEPARTMENT OF PUBLIC
WORKS & ENGINEERING

RESIDENTIAL STUCCO DETAILS
(WOOD FRAME)

1002 WASHINGTON AVE., HOUSTON, TEXAS 77002

APPROVED BY:
E. J. [Signature]

BUILDING OFFICIAL

DATE: 5/17/2016 DWG No: 16-03-R 1 of 1